

# Megaliner® Smooth Geomembrane

Megaplast High Density Polyethylene (HDPE) Geomembrane is manufactured with the highest quality resin specifically formulated and used in applications that require excellent chemical resistance and endurance properties.



## AT THE CORE:

An HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties

## Megaliner® PLATINUM 75

### Technical Data Sheet

This product specifications meet or exceed GRI GM 13

Sr. No.	Properties	Test Method (ASTM)	Unit (English)	Testing Frequency	MEGAPLATINUM 75
1.	Thickness - ((Nom - 5%) min. ave)	D 5199	mils	Every roll	30
	Lowest Individual Reading of 10 values				27
2.	Density (Min. Ave)	D 792	g/cc	Every 2,00,000 lb	0.940
	Melt Flow Index (MFI), 190°C /2.16 Kgf)	D 1238	g/10 min	Per batch / Lot	≤ 1.0
3.	Tensile Properties (min. ave) <sup>(Note 4)</sup>	D 6693 Type IV Dumbell, 2ipm	lb/in	Every 5th roll	120
	▶ Break Strength				63
	▶ Yield Strength				700
	▶ Break Elongation				13
	▶ Yield Elongation	G.L. 33mm	%		
4.	Tear Resistance (min. ave)	D 1004	lb	Every 10th roll	21
5.	Puncture Resistance (min. ave)	D 4833	lb	Every 10th roll	54
6.	Carbon Black Content (Range)	D 4218 / D 1603	%	Every 5th roll	2.0 - 3.0
7.	Carbon Black Dispersion	D 5596	category	Every 10th roll	Note 1
8.	Stress Crack Resistance (SP - Notched Constant Tensile Load)	D 5397 (Appendix)	Hrs.	Each two resign lots (One lot = 200,000 lb)	500
9.	Oxidative Induction Time (min. ave) Standard - OIT	D 3895 (at 200°C)	Minutes	Every 200,000 lb	> 100
	--OR-- High Pressure - OIT	D 5885 (at 150°C)			> 500
10.	Oven Aging at 85°C Standard - OIT (min. ave)- % retained after 90 days	D 5721 D 3895	%	Per each formulation	55
	--OR-- High Pressure - OIT (min. ave) - % retained after 90 days	D 5721 D 5885			80
11.	UV Resistance	D 7238	%	Per each formulation	50
	HP - OIT (min. ave) - % retained after 1600 hrs	D 5885			

Rev3 date: Jan - 2019	<b>Typical Roll Dimension</b> <sup>(Note 2)</sup>	
	<b>Roll Width, ft</b>	<b>23.5</b>
	<b>Roll Length, ft</b>	<b>1100</b>
	<b>Roll Area, Sq. ft</b>	<b>25850</b>

Note 1 : Dispersion only applies to near spherical agglomerates 9 to 10 views shall be category 1 or 2. No more than 1 view from category 3.

Note 2 : Roll length & widths have a tolerance of +/- 1%.

Note 3 : All geomembranes have dimensional stability of +/- 2% when tested according to ASTM D 1204.

Note 4 : Machine direction (MD) & Cross direction (XMD) average values should be on the basis of 5 specimens each direction.

## Megaplast USA Inc.